



Holbrook House, Little Waldingfield,
Sudbury, Suffolk CO10 0TH
Tel: (01787) 247595
e-mail: srl@srltsl.com

Contract: C/22162

Page: 1 of 1

Date: 26 April 2012


Confidential

See SRL report C/22162/R01 for full details

The Laboratory Measurement of Random Incidence Sound Absorption to BS EN ISO 354:2003

Client: Knauf AMF
Test Date: 29/03/2012
Empty Room: Temperature: 18.2 °C Humidity: 54 %RH Pressure: 1024 mbar
Room with Sample: Temperature: 17.5 °C Humidity: 44 %RH Pressure: 1024 mbar
Sample Description: Thermanex Alpha Varioline (steel pattern) 600x600x19mm
Mounting Method: E-200
Sample Area: 10.8 m²
Chamber Volume: 300 m³

Test 46				
Freq Hz	T1 sec	T2 sec	Absorp Coeff	Practical Absorp Coeff #
50*	4.65	3.52	0.31	
63*	4.28	3.18	0.36	n/a
80*	5.50	4.01	0.30	
100	6.79	4.15	0.42	
125	7.43	4.31	0.44	0.50
160	6.67	3.32	0.68	
200	7.13	3.33	0.72	
250	7.74	3.21	0.82	0.80
315	7.60	3.05	0.88	
400	6.84	2.92	0.89	
500	5.73	2.66	0.91	0.90
630	5.33	2.61	0.89	
800	5.80	2.69	0.90	
1000	6.23	2.81	0.88	0.95
1250	6.26	2.57	1.03	
1600	5.59	2.42	1.04	
2000	5.07	2.27	1.06	1.00
2500	4.48	2.11	1.06	
3150	3.73	1.90	1.05	
4000	3.10	1.65	1.09	1.00
5000	2.44	1.39	1.10	
6300*	1.73	1.09	1.07	
8000*	1.36	0.89	1.08	n/a
10000*	0.95	0.66	1.16	



α_w 0.95
Class A
 Calculated to EN ISO 11654:1997
 NRC 0.90
 Calculated to ASTM C 423-01
 * Denotes frequencies outside the range covered by BS EN ISO 354:2003
 T1, empty room reverberation time
 T2, room reverberation time with sample

Practical absorption coefficient, BS EN ISO 11654:1997

v4.2